



FLEX-A-BRAID

BRAIDED PACKING

FAB 5000

CARBON YARN IMPREGNATED W/PTFE, INTERLOCK BRAID

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	72	43	25	17	12	9	7.5	5.5	4.6	3.2	2.1	1.8
LBS/BOX	1 or 2	1 or 2	1 or 2	2	2 or 5	5	5	5	5	5 or 10	10	10



Temperature: To 600°F (315°C)
pH: 0-14 **Speed:** 3000 FPM
Pressure: Pumps-To 500 PSI (35 bar)
Construction: Interlock Braid

Carbon yarn packing heavily impregnated with PTFE dispersion. For severe services in pumps or valves handling chemicals, solvents and acids. An ideal packing for paper mill applications.

FAB 5010

CARBON YARN, W/BLOCKING AGENT AND GRAPHITE

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	160	58	39	21	15.3	11.7	8.8	7.8	6	4.1	3	2.2
LBS/BOX	1 or 2	1 or 2	1 or 2	2	2 or 5	5	5	5	5	5 or 10	10	10



Temperature: To 850°F - atmosphere (455°C)
Temperature: To 1200°F - steam (650°C)
pH: 0-14 **Speed:** 4000 FPM
Pressure: Pumps-To 500 PSI (35 bar)
Pressure: Valves-To 2500 PSI (170 bar)
Construction: Interlock Braid

Carbon yarn packing impregnated with graphite dispersion. For severe services in pump and valve applications, including super-heated steam, acids, alkalis, etc.

FAB 5020

PTFE FILAMENT, INTERLOCK BRAID (HARD, NO LUBRICANT)

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	74	32	20.6	13.5	9.5	7	5.5	4.1	3.3	2.5	2	1.6
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 0-14 **Speed:** 1000 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Pressure: Valves-To 2000 PSI (140 bar)
Construction: Interlock Braid

PTFE packing with PTFE dispersion. A dense firm packing used in valve and slow speed pump applications. Excellent chemical resistance.

FAB 5021

PTFE FILAMENT, LUBRICATED, INTERLOCK BRAID (SOFT)

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	72	31	19.4	12.5	9	7	5.1	4.1	3.3	2.3	1.7	1.2
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 0-14 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

PTFE packing treated with an inert lubricant. A soft and resilient packing for chemical pump and valve applications.

FAB5022**FDA PTFE FILAMENT, FOOD GRADE, INTERLOCK BRAID**

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	72	31	19.4	12.5	9	7	5.1	4.1	3.3	2.3	1.7	1.2
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 0-14 **Speed:** 1500 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Pressure: Valves-To 2000 PSI (140 bar)
Construction: Interlock Braid

Food Grade FDA PTFE filament, food grade, interlock braid with break-in lube.

FAB5030**GRAPHITE FILAMENT, INTERLOCK BRAID**

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	210	68	45	24	17	12.6	11	9.6	7.5	5.3	3.7	2.5
LBS/BOX	1 or 2	1 or 2	1 or 2	2	2 or 5	5	5	5	5	5 or 10	10	10



Temperature: To 850°F (455°C) - Atmosphere
Temperature: To 1200°F (650°C) - Steam
pH: 0-14 **Speed:** 4000 FPM
Pressure: Pumps-To 500 PSI (35 bar)
Pressure: Valves-To 2500 PSI (170 bar)
Construction: Interlock Braid

Graphite filament packing impregnated with a graphite dispersion. For severe service applications where leakage must be held to a minimum. Excellent chemical resistance.

FAB5031**100% GFO FIBER, INTERLOCK BRAID - BRANDED**

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	69	36	21	14	10	7	5.7	4.5	3.5	2.5	1.9	1.5
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10

*SEE 165LA FOR ECONOMICAL SUBSTITUTE



Temperature: To 550°F (285°C)
pH: 0-14 **Speed:** 4300 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Construction: Interlock Braid



Graphite filled PTFE fiber packing that improves thermal conductivity and will not harden. 100% GFO®.

*Trademark of W.L. Gore & Associates

FAB5032**PTFE/GRAPHITE FIBER, W/ARAMID CORNERS, INTERLOCK BRAID**

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	N/A	N/A	22	13.1	9.5	6.6	5.7	4.2	3.3	2.6	1.8	1.5
LBS/BOX	N/A	N/A	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 550°F (285°C)
pH: 2-12 **Speed:** 2500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

Unique packaging combining PTFE graphite with aramid corners. Aramid corners prevent rolls and extrusion. Excellent service pack-

FAB5033**PTFE/GRAPHITE FIBER, INTERLOCK BRAID (GFO LOOK-ALIKE)**

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	69	36	21	14	10	7	5.7	4.5	3.5	2.5	1.9	1.5
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 550°F (285°C)
pH: 0-14 **Speed:** 4300 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Construction: Interlock Braid

Graphite filled PTFE fiber with excellent thermal conductivity and will not harden. An economical substitute for Style 165.

FAB5034**100% GFO FIBER, INTERLOCK BRAID - BRANDED WITH CORE**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	69	36	21	14	10	7	5.7	4.5	3.5	2.5	1.9	1.5
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 550°F (285°C)
pH: 0-14 **Speed:** 4300 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Construction: Interlock Braid



Graphite filled PTFE fiber packing that improves thermal conductivity and will not harden. 100% GFO®. With Core.

*Trademark of W.L. Gore & Associates

FAB5040**ARAMID FILAMENT, LUBRICATED, INTERLOCK BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	78	37	22	16.5	11.4	8	6	4.9	3.6	2.6	2.3	1.6
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 3-11 **Speed:** 1900 FPM
Pressure: 500 PSI (35 bar)
Construction: Interlock Braid

Aramid fiber packing with an inert lubricant. Extremely durable, highly abrasive resistant packing. Ideal for slurry service.

FAB5050**SPUN ARAMID FIBER W/PTFE & LUB., INTERLOCK BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	75	35	20	18	10	8	6	5	3.8	2.4	2.1	1.7
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 2-12 **Speed:** 2250 FPM
Pressure: 500 PSI (35 bar)
Construction: Interlock Braid

Spun aramid fiber impregnated with PTFE dispersion and break-in lubricant. Ideal for valves and pumps in abrasive service.

FAB5060**PREM. FLAX, W/PTFE SQUARE PLAITED**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	120	50	30	20	15	10	8.6	6.6	5	3.6	2.7	2.1
LBS/BOX	2	2	5	5	5 or 10	5 or 10	5 or 10	5 or 10	10	10	10	10



Temperature: To 250°F (120°C)
pH: 4-9 **Speed:** 1500 FPM
Pressure: To 200 PSI (15 bar)
Construction: Square Braid

Premier marine service packing made with flax fibers and lubricated with PTFE dispersion. It has low friction and high tensile strength. Excellent for water service and paper mill applications.

FAB5061**FLAX, LUBRICATED, SQUARE PLAITED BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	139	59	28	21	14.8	10.7	8.6	6.5	5.1	3.5	2.6	2.3
LBS/BOX	2	2	5	5	5 or 10	5 or 10	5 or 10	5 or 10	10	10	10	10



Temperature: To 200°F (105°C)
pH: 5-9 **Speed:** 1200 FPM
Pressure: To 150 PSI (10 bar)
Construction: Square Plaited

Flax fiber packing lubricated with tallow and wax. Used for brine, cold water and oil service. Ideal for marine applications.

FAB5070 FLAX, PETROLEUM LUBRICATED & GRAPHITED, SQUARE PLAITED

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	118	58	33	22	15	11	9	7.4	5.7	3.8	2.8	2.3
LBS/BOX	2	2	5	5	5 or 10	5 or 10	5 or 10	5 or 10	10	10	10	10



Temperature: To 220°F (105°C)
pH: 5-9 **Speed:** 1200 FPM
Pressure: To 150 PSI (10 bar)
Construction: Square Braid

Flax fiber packing, treated with a petroleum-based lubricant and surface graphited.

FAB5071 FLAX, PETROLEUM LUBRICATED, NOT GRAPHITED, SQUARE PLAITED

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	118	58	33	22	15	11	9	7.4	5.7	3.8	2.8	2.3
LBS/BOX	2	2	5	5	5 or 10	5 or 10	5 or 10	5 or 10	10	10	10	10



Temperature: To 220°F (105°C)
pH: 5-9 **Speed:** 1200 FPM
Pressure: To 150 PSI (10 bar)
Construction: Square Braid

Flax fiber packing, treated with a petroleum-based lubricant.

FAB5080 BRAIDED FLEXIBLE GRAPHITE PACKING W/CARBON REINFORCED CORNERS

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB			33	21	14.8	10.5	8	7.2	5.7	3.8	3.2	2.5
LBS/BOX			1 or 2	2	2 or 5	5	5	5	5	5	4	3



Temperature: To 1250°F (650°C) - Steam
Temperature: To 1050°F (565°C) - Atmosphere
pH: 0-14 except strong oxidizers
Speed: 4000 FPM
Pressure: 3000 PSI (200 bar)
Construction: Interlock Braid

Braided from a combination of expanded flexible graphite (1100TCP) and high strength carbon fibers (90). Carbon fibers are braided into the corners to provide anti-extrusion and better abrasion resistance in tough applications. Can give virtually leak free performance. 1100CR was independently fire tested to API 589 at API 607 temperatures and pressures.

FAB5081 CHEMGRAPH TCP - BRAIDED FLEXIBLE GRAPHITE PACKING

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	103	48	33	20	12	10	7	6	5	3.3	2.5	2
LBS/BOX	N/A	N/A	1 or 2	2	2 or 5	5	5	5	5	5	4	3



Temperature: To 1200°F (650°C) - Steam
Temperature: To 850°F (455°C) - Atmosphere
pH: 0-14 except strong oxidizers
Speed: 4000 FPM
Pressure: To 3000 PSI (200 bar)
Construction: Interlock Braid

Braided from pure expanded graphite. It is resilient, self-lubricating, chemically inert and thermally conductive. 1100TCP can be used in both pumps and valves in a wide range of service conditions.

FAB 5082 BRAIDED FLEXIBLE GRAPHITE W/INCONEL WIRE, API 589 & 607 FIRE TESTED

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	110	50	30	20	13	10	7	6.4	5	3.3	2.6	2
LBS/BOX	1	1	1 or 2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 1200°F (650°C) - Steam
Temperature: To 850°F (455°C) - Atmosphere
pH: 0-14 except strong oxidizers
Pressure: 3000 PSI (200 bar)
Construction: Interlock Braid

Braided from a combination of expanded flexible graphite and inconel wire. 110 I retains dimensional stability in high temperature, high pressure environments, and can meet most VOC emission control regulations. 1100 I was independently fire tested to API 589 at API 607 temperatures and pressures.

FAB 5090 PREMIUM SYNTEX FIBER END COATED W/PTFE, BREAK-IN-LUBE, INTERLOCK BRAID

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	80	48	25	16.6	12	8.5	6.4	5.7	3.6	2.6	2.6	1.7
LBS/BOX	1	1	2 or 5	2 or 5	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C) **Special syntex fiber, with each strand impregnated with PTFE dispersion both prior to and after braiding. Finished packing also has a break-in lubricant. An asbestos replacement packing for general service applications. Good chemical resistance.**
pH: 0-12 **Speed:** 2200 FPM
Pressure: To 500 PSI (35 bar)
Construction: Interlock Braid

FAB 5091 SYNTEX FIBER, W/ARAMID CONERS, BREAK-IN-LUBE, INTERLOCK BRAID

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB			25	17	11.7	8.8	6.8	5.7	4.2	3.2	2.1	1.6
LBS/BOX			2 or 5	2 or 5	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C) **Unique packing combining 1152 and 170 fibers. Aramid corners prevent roll and extrusion. Well suited for abrasive applications and end rings with other**
pH: 3-12 **Speed:** 2200 FPM
Pressure: To 500 PSI (35 bar)
Construction: Interlock Braid

FAB5100 SYNTEX FIBER, W/PTFE, BREAK-IN-LUBE, INTERLOCK BRAID (GENERAL SERVICE)

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	80	42	20	13	8.8	7.6	5.7	5	4.2	2.5	2.1	1.5
LBS/BOX	1	1	2 or 5	2 or 5	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C) **Syntex fiber thoroughly impregnated with PTFE, a break-in lubricant is added for start-up. An economical PTFE general service packing. Interlock braid.**
pH: 2-10 **Speed:** 2000 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

FAB 5110 KYNOL/PTFE, WITH BREAK-IN-LUBE, INTERLOCK BRAID

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	80	50	26	19	13	10	7.4	6	4.6	3.2	2.5	1.9
LBS/BOX	1	1	2	2 or 5	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C) **Special Kynol™ fibers treated with PTFE and break-in lubricant. This is a non-contaminating packing for use in paper mills in almost all pump and valve ap-**
pH: 0-13 **Speed:** 1500 FPM
Pressure: To 500 PSI (35 bar)
Construction: Interlock Braid

FAB 5120 SYNTEX FIBER, LUBRICATED & GRAPHITED, INTERLOCK BRAID

SIZE	^1/8"	^3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	128	56	31	21	16	11	8.6	6.7	5.8	4	3	2.1
LBS/BOX	2	2	2	2 or 5	2 or 5	5	5	5	5 or 10	10	10	10



Temperature: To 500°F (265°C) **Syntex fiber packing thoroughly impregnated with a high temperature lubricant. Finished packing is surface graphited. An asbestos replacement packing for general service use on pumps and valves.**
pH: 4-10 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

With MOLLY lubrication : **FAB 5122**

FAB 5121**SYNTEX FIBER, LUBRICATED, NOT GRAPHITED, INTERLOCK BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	128	56	31	21	16	11	8.6	6.7	5.8	4	3	2.1
LBS/BOX	2	2	2	2 or 5	2 or 5	5	5	5	5 or 10	10	10	10



Temperature: To 500°F (265°C)
pH: 4-10 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

Syntex fiber packing thoroughly impregnated with a high temperature lubricant. An asbestos replacement packing for general service use on pumps and valves.

FAB 5130**NON-ASBESTOS HI-TEMP FIBER W/INCONEL**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	76	39	25	12.6	9.4	7.1	6	4.4	3.8	2.6	2.1	1.5
LBS/BOX	1	1	2 or 5	2 or 5	2 or 5	5	5	5	5	10	10	10



Temperature: To 1200°F -
 Steam (650°C)
pH: 1-12
Pressure: To 2500 PSI (17 bar)
Construction: Braid over core

High temperature carbon yarn with inconel wire braided over a resilient core thoroughly impregnated with graphite and corrosion inhibitor.

FAB 5132**DRY FIBERGLASS, SQUARE PLAITED**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB			28	18	12.5	10	7.7	6.2	5.4	3.8	2.6	2.1
LBS/BOX			2 or 5	2 or 5	5	5	5 or 10	5 or 10	10	10	10	10



Temperature: To 1000°F (535°C)
pH: 2-11
Construction: Square Plaited

Textured fiberglass fiber packing. It is braided dry with no lubricant. Packing will not swell, shrink and is completely incombustible. Used for sealing over doors. Excellent chemical resistance.

FAB 5133**DRY FIBERGLASS, INTERLOCK BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
PRICE/LB							8	6	4.2	3.3	2.5	2
FT/LB							5 or 10	5 or 10	10	10	10	10

Temperature: To 1000°F (535°C)
pH: 2-11
Construction: Interlock Braid

Interlock Braided Texturized fiberglass fiber packing. It is braided dry with no lubricant. Packing will not swell, shrink and is completely incombustible. Used for sealing over doors. Excellent chemical resistance. Available from 1/2" to 1"

FAB 5140**SYNTEX FIBER, LUBRICATED & GRAPHITED SQUARE PLAITED BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	128	56	34	22	16	12.5	9	6	5.5	4	2.6	2.2
LBS/BOX	2	2	2 or 5	2 or 5	5	5	5	5 or 10	5 or 10	10	10	10



Temperature: To 500°F (260°C)
pH: 4-10 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Square Plaited

Syntex fiber packing treated with a high temperature lubricant and graphited. Soft and pliable for general service on pumps and valves.

FAB 5141**SYNTEX FIBER, LUBRICATED, NOT GRAPHITED SQUARE PLAITED BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	128	56	34	22	16	12.5	9	6	5.5	4	2.6	2.2
LBS/BOX	2	2	2 or 5	2 or 5	5	5	5	5 or 10	5 or 10	10	10	10



Temperature: To 500°F (260°C)
pH: 4-10 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Square Plaited

Syntex fiber packing treated with a high temperature lubricant. Soft and pliable for general service on pumps and valves. Not graphited.

FAB 5150**WHITE META-ARAMID W/PTFE AND BREAK-IN-LUBE**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	90	50	26	18	10	8	6.2	5.1	4.1	3.2	2	1.6
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 500°F (260°C)
pH: 4-10 **Speed:** 1500 FPM
Pressure: To 300 PSI (20 bar)
Construction: Interlock Braid

Special meta-aramid fiber with PTFE and break-in lubricant. Very conformable and abrasive resistant. Highly resistant to degradation and chemical attack. For use in agitators, stock pumps, mixers, etc.

FAB 5160**PTFE/GRAPHITE FIBER, INTERLOCK BRAID**

SIZE	1/8"	3/16"	1/4"	5/16"	3/8"	7/16"	1/2"	9/16"	5/8"	3/4"	7/8"	1"
FT/LB	63	42	20	12.5	9.3	6.8	5.4	4	3.2	2.4	1.7	1.3
LBS/BOX	1	1	2	2	2 or 5	5	5	5	5	10	10	10



Temperature: To 550°F (285°C)
pH: 0-14 **Speed:** 4500 FPM
Pressure: Pumps-To 300 PSI (20 bar)
Construction: Interlock Braid

Special blend of PTFE and graphite fibers plus a high temperature lubricant. An economical substitute for style 165. Good chemical and abrasion resistant packing.



^INDICATES SQUARE PLAITED

FLEX-A-SEAL 2012

NON-STANDARD LUBRICATION AVAILABLE:
 SURFACE GRAPHITE
 MOLY LUBRICATION

\$50.00 MINIMUM ORDER

7

FLEX-A-BRAID: BRAIDED PACKING